

Sintered Silicon Carbide Ceramic
 Technical Parameter of SSIC products

Item	Unit	Data
temperature of application	°C	1600
density	g/cm ³	>3.1
open porosity	%	<0.1
bending strength	Mpa	>400
	Mpa	
modulus of elasticity	Gpa	420
	Gpa	
thermal conductivity	W/m.k	74
coefficient of thermal expansion	k ⁻¹ × 10 ⁻⁶	4.1
Vickers Hardness HV ₁₀	Gpa	22
acid-proof alkaline		Excellent

The values for above are the typical result from the test,not the promised exactly data applied to all orders

CERATEK TECHNICAL CERAMIC CO., LIMITED
 Tel/Fax:+86 21 33876960 Mobile:+86 13818729891
 Email:info@ceratek.net Web:www.ceratek.net